

Powerdeck® U

Powerdeck U is a thermal insulation board. Its core consists out of rigid polyisocyanurate PIR foam. The board is faced with a bituminous coated glass fleece on both sides.

Application(s)

Thermal insulation used in warm flat roofs. The board can be used in mechanical fixed and adhered systems in appropriate build-ups combined with bituminous and single-ply waterproofing systems.

Board

Description	Value	Unit	Tolerances	Standard
Dimensions				
Length	1200	mm		
Width	600	mm		
Thickness range	20 - 150	mm	T2	EN 823
Density (core volume weight)	± 30	kg/m³		
Appearance				
Facing	Bituminous coated glass fleece on both sides.			
Edge finishing	Straight edges			

Essential characteristics

Description	Standard	EN code	Value	Unit
Thermal conductivity (declared value)				
≥ 120 mm	EN 13165	λ _D	0.024	W/mK
80 – 119 mm	EN 13165	λ _D	0.025	W/mK
≤ 79 mm	EN 13165	λ _D	0.026	W/mK
Mechanical properties				
Compressive stress or compressive strength at 10% deformation	EN 826	CS(10/Y)150	≥150	kPa
Dimensional stability under specified temperature and humidity conditions				
48 hrs 70°C, 90% RH	EN 1604	DS(70,90)3		
48 hrs -20°C	EN 1604	DS(-20,-)1		

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Zuidstraat 15, 8560 Wevelgem, Belgium

www.recticelinsulation.com

FEEL
GOOD
INSIDE

RECTICEL
insulation

Deformation under specified compressive load and temperature conditions

load and temperature conditions	EN 1605	DLT(2)5	≤5	%
Tensile strength perpendicular to faces	EN 1607	TR80	≥80	kPa

Fire behaviour

Reaction to fire (product as such)	EN 13501-1	Euroclass	F	
------------------------------------	------------	-----------	---	--

Hygrometric properties

Water vapour diffusion coefficient (tabulated value)	EN150 10456	μ	50 - 100	
Long term water absorption by total immersion	EN 12087	WL(T)2	≤2	vol-%

Insulation Values

Thickness (mm)	λD-value (W/mK)	RD-value (m²K/W)
20	0.026	0.75
30	0.026	1.15
40	0.026	1.50
50	0.026	1.90
60	0.026	2.30
70	0.026	2.65
80	0.025	3.20
90	0.025	3.60
100	0.025	4.00
120	0.024	5.00
130	0.024	5.40
140	0.024	5.80
150	0.024	6.25

Standards & Certificates

Standards

Product standard	EN 13165:2012 + A2:2016
Production	ISO 9001:2015
Environmental management	ISO 14001:2015

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Zuidstraat 15, 8560 Wevelgem, Belgium

www.recticelinsulation.com

FEEL
GOOD
INSIDE

RECTICEL
insulation

Certificates

BBA

13/5045

(20-160mm)

Other / Miscellaneous**Production plant**

Stoke-on-Trent

Enterprise Way, Meir Park, Stoke-on-Trent, ST3 7UN

Storage/handling

Stock dry and protected from direct sunlight

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Zuidstraat 15, 8560 Wevelgem, Belgium

www.recticelinsulation.comFEEL
GOOD
INSIDE **RECTICEL**
insulation